

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09J 153/02, 157/02	A1	(11) International Publication Number: WO 95/16755 (43) International Publication Date: 22 June 1995 (22.06.95)
(21) International Application Number: PCT/US94/14384 (22) International Filing Date: 13 December 1994 (13.12.94) (30) Priority Data: 08/167,545 15 December 1993 (15.12.93) US 08/345,103 28 November 1994 (28.11.94) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US). (72) Inventor: JACOB, Lutz, Erich; Lijsterlaan 17, B-3080 Ter- vuren (BE). (74) Agents: MULLER, William, G. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522 (US).		(81) Designated States: CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: LOW VISCOSITY HOT MELT PRESSURE SENSITIVE ADHESIVE COMPOSITIONS (57) Abstract A low melt viscosity hot melt pressure sensitive adhesive composition having enhanced tack properties is provided. The composition is based on an S-I-S block copolymer having polystyrene and polyisoprene block segments blended with a petroleum tackifier resin which is the Friedel Crafts polymerization product of (i) a cracked petroleum feed containing C ₅ olefins and diolefins or a mixture of C ₅ and C ₆ olefins and diolefins copolymerized with (ii) from about 5 to 15 % by weight of a monovinyl aromatic monomer having 8 or 9 carbon atoms, e.g., styrene. The composition optionally also includes a polystyrene - polyisoprene diblock copolymer and a processing oil. The composition may be readily applied as solvent-free melt to various substrates using coating die technology because of its low melt viscosity at coating temperatures.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

**LOW VISCOSITY HOT MELT PRESSURE SENSITIVE ADHESIVE
COMPOSITIONS**

5 This invention relates to low viscosity, hot melt, pressure sensitive adhesive compositions which can be applied to substrates as a melt using high speed coating equipment.

Hot melt pressure sensitive adhesive compositions based on thermoplastic block copolymers derived from a monovinyl aromatic hydrocarbon and a conjugated diolefin mixed with a tackifying resin are well known in the art.
10 Typically such compositions contain a block copolymer of the A-B-A type as a base polymer, wherein A is typically a polymerized styrene block and B is typically a polymerized block of isoprene or butadiene, said copolymer generally having a number average molecular weight in the range of from about 25,000 to about 500,000. Mixtures of these block polymers with appropriate amounts of a tackifier
15 resin, such as a terpene or rosin-type resin, and a processing oil provide compositions which combine good adhesive and cohesive properties, thereby rendering them particularly useful as hot melt pressure sensitive adhesives.

Examples of such prior art hot melt pressure sensitive adhesives (HMPSA) are found in a number of prior art patents. For example, U.S. Patents 4,411,954
20 and 4,699,941 disclose HMPSA based on a mixture of an A-B-A styrene-isoprene-styrene block copolymer blended with a tackifying resin and an antioxidant. A preferred disclosed tackifying resin is one derived from a polymerized mixture of aliphatic dienes and C₅ or C₆ monoolefins. U.S. Patent 4,104,327 discloses pressure sensitive adhesive compositions based on styrene-butadiene or styrene-
25 butadiene-styrene block copolymers, mixed with an optional styrene-isoprene or styrene-isoprene-styrene block copolymer and further containing, as a tackifier, a hydrocarbon resin containing from 49-95% by weight of 1,3-pentadiene units and from 60 to 5% by weight of alpha-methylstyrene units in the polymer chain and having a softening point of 60°C to 140°C.

30 In addition, pressure sensitive adhesive compositions are also disclosed in the art which contain petroleum resins based on copolymers of a feed comprising predominantly C₅ and C₆ monoolefins and diolefins and up to about 30 wt% of a monovinyl aromatic compound as a tackifying resin. For Example, U.S. Patent 4,623,698 discloses aqueous - based pressure sensitive adhesive compositions
35 based on a mixture of a carboxylated styrene/butadiene copolymer and such a petroleum tackifying resin. U.S. Patent 4,078,132 discloses similar petroleum

- 2 -

resins used to tackify various elastomeric polymers and copolymers.

While these and other HMPSA compositions are suitable as adhesives in various applications, these compositions are not ideally suited for use in conjunction with high speed (>500 meters/min) HMPSA coating machines. The HMPSA must pass thin channels in the coating die associated with such machines. Since allowable pressure in these dies is limited, the viscosity of the HMPSA composition at coating temperatures (150°C up to about 180°C) becomes a key issue. If the melt viscosity of the composition is too high, equipment normally used to apply a melt to a substrate can not be effectively used. Viscosity of the HMPSA can be reduced by the inclusion of high loadings of processing oils or solvents into the composition, but inclusion of high loadings of processing oil tends to diminish the desirable adhesive and cohesive properties of the HMPSA and inclusion of solvents tends to add to the expense of the coating operation, increased fire hazards and requires solvent recovery equipment for environmental purposes.

SUMMARY OF THE INVENTION

The invention provides for a low melt viscosity, solvent free, hot melt pressure sensitive adhesive composition which exhibits both excellent cohesive and adhesive strength, said composition comprising a mixture of.

a) 100 parts by weight of a thermoplastic elastomer having the structure $(S-I)_n-1S$ wherein S is substantially a polystyrene block, I is substantially a polyisoprene block and n is an integer of from 2 to 10 and wherein the content of polystyrene in said thermoplastic elastomer ranges from about 10 to about 30% by weight and wherein the number average molecular weight of said thermoplastic elastomer ranges from about 50,000 to about 500,000;

b) from about 70 to about 150 parts by weight of a petroleum resin tackifier having a softening point in the range of from about 85°C to about 105°C, said resin being a Friedel Crafts copolymer comprising:

i) a petroleum feed comprising C₅ olefins and C₅ diolefins or a mixture of C₅ and C₆ olefins and diolefins, said feed being obtained from the cracking of petroleum feedstock, copolymerized with

ii) from about 5 to 15% by weight, based on component (i), of one or a mixture of monovinyl aromatic compounds having 8-9 carbon atoms;

said composition characterized as having a melt viscosity at 175°C of less than about 100,000 mPa.s as measured by ASTM-D3236.

The composition of the present invention is suitable for application to a

- 3 -

suitable substrate for the production of adhesive tapes which are particularly useful for effective sealing of packaging materials, especially corrugated cardboard containers.

5 DETAILED DESCRIPTION OF THE INVENTION

The block copolymer used as the base elastomer component of the adhesive composition of the invention is preferably a triblock copolymer of the above formula wherein $n = 2$, i.e., is a linear polymer of the formula S-I-S wherein S is substantially a polystyrene block and I is substantially a polyisoprene block. These
10 block copolymers may be prepared by well known anionic solution polymerization techniques using lithium-type initiators such as disclosed in U.S. Patents 3,251,905 and 3,239,478, the complete disclosure of which patents is incorporated herein by reference.

Preferred block copolymers have a number average molecular weight
15 (determined by GPC) in the range of from about 50,000 to 500,000, more preferably from about 90,000 to about 250,000, even more preferably 90,000 to 175,000, and most preferably 90,000 to 135,000. These block copolymers contain from about 10 to 30% by weight of polymerized styrene, more preferably from about 15 to 25% by weight polymerized styrene and most preferably from about
20 16-20% by weight polymerized styrene.

The block copolymer component may also comprise a blend of two different block thermoplastic elastomers, one having a polystyrene block content of 10-20% by weight and the other having a different polystyrene block content of from 15-35% by weight, blended in a ratio in the range of from about 10:1 to 1:10
25 parts by weight. The use of two different block copolymers offers the advantages of improved cohesive strength and more precisely tailoring polystyrene content in the preferred target range of from about 15 to 25%, or 16-20% by weight respectively.

Though a pure triblock copolymer is preferred (one having less than 0.1 wt. of diblock polymer) the composition may also contain from about 0.1 to about 10
30 wt.%, preferably less than or equal to 6 wt.%, most preferably less than 5 wt.% of triblock copolymer of a di-block copolymer having the structure S-I and containing from about 10 to 30 % by weight of the polystyrene block. This material may be present as an impurity in the manufacture of the triblock copolymer or may be
35 separately blended with the triblock as a further technique for achieving target polystyrene content or modifying the cohesive properties of the composition.

- 4 -

Preferred number average molecular weight of the di-block copolymer ranges from about 40,000 to about 250,000.

These linear and radial block copolymers are available commercially and are prepared in accordance with methods known in the art. See the disclosures of U.S. patents 5,143,968, 5,292,819 and 5,358,783, each of which is incorporated by reference for purposes of U.S. patent practice.

Particularly preferred block copolymers used in this invention have a melt flow rate in the range of from about 5 to 20 g/10 min, more preferably from about 10 to 18 g/10 min., as measured by ASTM D 1238 - 82 using condition G (200°C., 5kg. weight).

The petroleum resins used as tackifier according to the present invention are prepared by the polymerization of a mixture of a petroleum cracked distillate generally boiling in the range 25°C to 80°C and a monovinyl aromatic monomer having 8 or 9 carbon atoms in the proportions to yield a resin containing from 5-15 wt.% of the monovinyl aromatic compound as determined by Nuclear Magnetic Resonance analysis. The petroleum cracked distillate comprises a mixture of saturated and unsaturated monomers, the unsaturated monomers being mono-olefines and diolefines and, although the unsaturated materials are predominantly C₅, some higher and lower materials such as C₆ olefines and diolefines may be present. The distillate may also contain saturated or aromatic materials which can act as a polymerization solvent.

The preferred monovinyl aromatic monomer is styrene which may be substituted in the aromatic group. Alternatively alpha-methyl styrene or vinyl toluene may be used. It is however, preferred for color reasons to use the pure monomer rather than the commercially available mixtures of vinyl aromatic monomers.

The resins are conveniently prepared by Friedel-Crafts catalyzed polymerization in which the mixture of cracked distillate and monovinyl aromatic monomer are treated with 0.25-2.5 wt.% of a catalyst such as aluminum chloride, aluminum bromide, or solutions, slurries or complexes thereof or borontrifluoride. The polymerization mixture may also include from about 10 to 100 wt% of a chain transfer agent such as a diisobutene oligomer to obtain resins having a narrower molecular weight distribution. These reactions are generally carried out at temperatures in the range 0° to 120°C., preferably 0° to 80°C., more preferably 20° to 55°C, the conditions being controlled to yield a resin of the required softening point. Residual catalyst is quenched by suitable methods such as addition

- 5 -

of methyl alcohol and subsequent filtration followed by water and/or caustic washing. The final solution may then be stripped of unreacted hydrocarbons and low molecular weight oils by vacuum or steam distillation.

5 The most preferred tackifier resins have ring and ball softening points in the range of from about 85°C to about 105°C, more preferably in the range of from about 90°C to about 100°C and a content of monovinyl aromatic monomer, e.g., styrene, in the range of about 6-12 wt%.

A particularly preferred tackifier for use in the present invention has the following typical properties:

10

Softening Point (°C)	92
Gardner Color	3
Styrene content (NMR) %	7-10
Mn (number average MW)	1150
Mw (weight average MW)	1840
Mw/Mn (molecular weight distribution)	1.6
Mz (viscosity average MW)	2800

These resins and their method of manufacture are more generally disclosed in U.S. Patent 4,078,132, the complete disclosure of which is incorporated hereby by reference for the purpose of U.S. patent practice.

15 The quantity of resin tackifier used in combination with the block copolymer may range from about 70 to about 150 parts by weight per 100 parts by weight of the block copolymer. A more preferred level of addition is in the range of from about 90 to about 125 parts by weight per 100 parts by weight of block copolymer.

20 The adhesive composition may also include other additives as known in the art such as hydrocarbon extender oils, antioxidants, colorants, fillers and the like.

Suitable extender oils include aromatic, naphthenic or paraffinic oils and mixtures thereof. One of the particular advantages of the invention is that none or only minor amounts of extender oil may be required to achieve good flow and coating characteristics because of the inherently low melt viscosity properties of the adhesive of the invention. Reduction in the level of extender oil required to process the composition tends to result in improved cohesiveness of the adhesive and reduces bleed out of the extender. Where used, the extender oil is added at a level from about 0.5 to about 25 parts by weight per hundred parts by weight of

25

- 6 -

the block copolymer, more preferably from about 5 to 15 parts by weight.

Suitable antioxidants include hindered phenols such as 2,6-di-t-butyl-4-methylphenol; 1,3,5-trimethyl-2,4,6-tris (3',5'-di-t-butyl-4'-hydroxybenzyl)-benzene; tetrakis [(methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate))] methane
5 (IRGANOX™ 1010); octadecyl-3,5-di-t-butyl-4-hydroxy cinnamate (IRGANOX™ 1076); and like known materials. Where present, the antioxidant is used at a preferred level of from about 0.05 to about 2 parts by weight per 100 parts by weight of block copolymer.

As indicated above, the components forming the adhesive formulation of
10 the invention have properties such that adhesives having a very low melt viscosity are provided, thereby facilitating flow of the adhesive through the coating apparatus, e.g., coating die, without resorting to the inclusion of solvents or excess extender oil into the composition. Melt viscosities of from about 35,000 to less than about 100,000 milli Pascal second (mPa.s or CPS) measured at 175°C per
15 ASTM D 3236 can be readily achieved. The more preferred melt viscosity at 175°C is less than 80,000 m.Pas and the most preferred melt viscosity at 175°C lies in the range of from about 35,000 to about 50,000 mPa.s.

Highly efficient manufacturing processes are made possible through use of the adhesive formulations of the invention since high speed coating means can be
20 used. For example, the manufacture of tapes from oriented polypropylene film requires coating application speeds of at least 250 m/min. The formulations of the invention are capable of application up to 750 m/min. or more, and the high speed efficiency processes of this invention can utilize preferred coating speeds of 500 m/min. and up.

25 The components of the adhesive composition may be blended by mixing them using any suitable mixing device at a temperature above the melting point of the components, e.g., at 130 to 180°C for a period of time sufficient to form a homogeneous mixture, normally 1 to 120 minutes depending on the type of mixing device.

30 The adhesive composition of the present invention may be applied to a substrate as a melt and then cooled using conventional procedures. The substrate used depends upon the use envisaged but it is usually a relatively thin material, usually no greater than about 3.2 mm in thickness, and in the manufacture of tapes and labels the substrate is a relatively thin sheet material. The sheet material may
35 be a polymeric material which is flexible at room temperature. The sheet material may be a homopolymer of an ethylenically unsaturated monomer such as ethylene,

- 7 -

propylene or vinyl chloride, or be polyester or polyamide provided it has sufficient flexibility for the desired end use. Alternatively the substrate may be made from cellulosic or reconstituted cellulosic material such as rayon. The substrate need not be a sheet material but may be composed of fibers which may be woven, or non woven as is the case in paper. Woven substrates may be made from cellulosic material, such as cotton or from fibers of any of the above mentioned polymers.

The composition is applied to the substrate using conventional coating techniques such as roller coaters, die coaters and blade coaters, generally at a temperature in the range of from about 150°C to 200°C. For example, the ready mixed HMPSA heated to the temperature where it will flow readily, usually at temperatures from 170°C to 190°C, can be applied to a flexible backing by any of know techniques, preferably using a slot die.

A slot die is a closed system where the HMPSA is pumped through by a positive displacement pump. The slot die usually includes a rotating bar at the point of the outlet of the HMPSA in order to obtain a smooth coating surface.

Due to required thin channels inside the die through which the HMPSA has to flow, it is obvious that there are melt viscosity limits for the HMPSA depending on required throughput. Thus one can say that, the higher the coating speed is, the lower the melt viscosity needs to be to obtain consistent and even coating at the desired thickness onto the web.

The substrate should be coated with sufficient composition to provide a dry coat weight from about 10 to about 65 g/cm². Generally in the manufacture of tapes using a continuous sheet polymeric substrate, a dry coat weight of about 10-30 g/m² is used. In the manufacture of labels, a dry coat weight from about 10 to 30 g/cm² is usually used. In the manufacture of masking tape a dry coat weight from about 35 to about 65 g/cm² is usually used.

After coating, the coated substrate is cut to the required dimension. In the manufacture of tape the substrate is cut into strips and rolled to provide a finished product. The substrate may also be cut into shaped items to provide labels or medicinal tapes.

The following examples are illustrative of the invention. Materials used in preparing the adhesive compositions as identified in the examples are as follows:

- 8 -

- V4111 SIS - A linear polystyrene-polyisoprene-polystyrene triblock copolymer supplied by Dexco Polymers having a styrene content of 17.5 - 19.0 % by weight, melt flow rate of 9.7 - 13.8 g/10 min., a number average mol. wt. of 125,000 \pm 2%, and 0 wt.% diblock (SI).¹
- DPX 511 SIS - A linear polystyrene-polyisoprene-polystyrene triblock copolymer supplied by Dexco Polymers having a styrene content of 17.5 to 19.0% by weight, melt flow rate of 14.5 - 17 g/10 min., number average mol. wt. of 110,000 \pm 2%, and 0 wt.% diblock (SI).¹
- CARIFLEX ®
TR 1107 - A polystyrene-polyisoprene-polystyrene triblock copolymer of Shell Chemical being a styrene content of 15 wt.%, diblock (SI) content of 18 wt.%, 0 melt flow rate 9 g/10min., and number average mol. wt. of 160,000.¹
- QUINTACK ®
3450 - A radial polystyrene-polyisoprene-polystyrene from Nippon Zeon having 20 wt.% styrene, 30 wt.% di-block content, melt flow rate of 15 g/10 min., and number average mol. wt. of 180,000.¹
- E - 1310 - Petroleum resin available under the trade name ESCOREZ™ from Exxon Chemical Company and containing about 0.3% by weight of polymerized styrene and having a softening point of about 93.5°C.

¹ Note: styrene contents, molecular weights and melt flow rates were measured in accordance with the methods described in U.S. patent 5,143,968.

- 9 -

- E - 2203 - Petroleum resin available under the trade name ESCOREZ™ from Exxon Chemical Company and containing about 8-10% by weight of polymerized styrene, and having a softening point of about 92°C and a number average molecular weight of about 1150.
- WINGTACK®
EXTRA - Petroleum resin available from Good Year containing about 6.9% by weight of polymerized styrene and having a softening point of about 99.2°C.
- FLEXON® 876 - A paraffinic extender oil available from Exxon Chemical Company.
- SI-Diblock - A polystyrene - polyisoprene di-block copolymer containing about 18% by weight polymerized styrene.
- ANTIOXIDANT - IRGANOX® 1076, a phenolic compound of CIBA GEIGY

The various test methods identified in the Tables are as follows:

Ball Tack is measured by Pressure Sensitive Tape Council (PSTC) test 6.

180° Peel Strength is measured by PSTC-1 test.

5 Loop Tack is measured by the FINAT-9 test.

Viscosity is measured by ASTM D-3236 test.

Hot shear is measured by suspending a 1000 gram weight from a 25 mm wide strip of MYLAR™ polyester film coated with the adhesive formulation which is adhered to a stainless steel plate or corrugated cardboard surface with a contact area of 12.5 mm. x 25mm. The sample is placed in a ventilated oven at 40°C. Time is recorded until stress failure occurs. Typically, these tests are made and recorded individually to determine reliability of the holding power.

10 Shear Adhesion Failure Temperature (SAFT) is determined by adhering a coated MYLAR strip of 25 mm. width to stainless steel with a contact area of 12.5 mm. x 25 mm., hanging the samples in an oven held at 25°C and suspending a 500

gram weight from the bottom of the strip. The temperature is raised at 0.4C°/min and the bond failure temperature is measured. The Shear Adhesion Temperature is the average of three tests.

5 **Examples 1-11**

A series of adhesive compositions both within and outside the scope of the invention were prepared by mixing ingredients as set forth in Table 1 in a two blade mixer at 145°C for a period of 70 minutes. The composition was then heated to about 190°C and the melt was pumped through a coating die onto a 36 micron MYLAR™ polyester film. The dry weight of the applied coating layer ranged from about 19 to 24 g/m². After coating, the tacky side of the film was laminated to a release paper and the film was wound and cut.

Formulation and physical property data for the various formulations are shown in Table 1.

As is evident from the physical property data of Table 1, compositions within the scope of the invention show generally enhanced ball tack and 40°C shear properties as compared with compositions containing a low styrene content tackifier resin. In addition, lower melt viscosities are achieved as evidenced by both Brookfield and Haake viscosity data. Haake data allows a more elaborate evaluation of the viscosity of materials because absolute viscosity is recorded as a dynamic function based on shear rate, as a function of time and as a function of temperature.

Examples 12-15

25 Four additional adhesive compositions were prepared in accordance with the method of Examples 1-11 and adhesive and viscosity data was obtained. These formulations and data are shown in Table 2, which also includes comparative data from Examples 1 and 2.

These examples 12-15 illustrate that inclusion of 6 parts by weight of a polystyrene-polyisoprene diblock copolymer has very little effect on the good tack, shear and viscosity properties of the composition. A comparison with examples 1 and 2 once again illustrates that low styrene or styrene-free tackifier resins provide an adhesive with inferior tack and shear properties, as well as higher melt viscosity.

35 **Examples 16-19**

The four examples of Table 3 illustrate a direct comparison of two linear

- 11 -

SIS polymers in identical compositions prepared as for Examples 1-11 above. The DPX 511 SIS polymer being pure triblock (no significant diblock) exhibits both higher shear on cardboard at 40°C and lower melt viscosity.

5

Examples 20-22

10 These examples of Table 4 compare a commercially available radial triblock copolymer with two linear triblock copolymers. Each example was formulated at 100 parts block polymer, 120 parts Escorez® 2203, 10 parts Flexon® 876, and 1 part antioxidant. The blend formulations were mixed for 70 min. at 145°C and coated on mylar at a thickness of 23 microns, coating weight of 18-20 g/m². Each sample was covered with release coated oriented polypropylene film before being applied. Improved shear on cardboard at 40°C, SAFT and loop tack was observed with the linear block copolymers while decreased viscosity was observed for the radial block copolymer.

TABLE I

FORMULATION	EX. 1*	EX. 2	EX. 3	EX. 4*	EX. 5	EX. 6	EX. 7*	EX. 8*	EX. 9*	EX. 10	EX. 11
V-4111 SIS	100	100	100	--	--	--	100	--	100	100	--
DPX-511 SIS	--	--	--	100	100	100	--	100	--	--	100
E 1310	120	--	--	120	--	--	100	100	60	--	--
E 2203	--	120	--	--	120	--	--	--	40	100	100
WINGTACK EXTRA	--	--	120	--	--	120	--	--	--	--	--
FLEXON 876	10	10	10	10	10	10	--	--	--	--	--
ANTIOXIDANT	1	1	1	1	1	1	1	1	1	1	1
180 PEEL STRENGTH											
(N/CM) -steel	7.73	7.73	8.07	7.60	7.80	8.20	NT	NT	NT	NT	NT
LOOP TACK (H/25mm) -steel	25.4	30.3	27.5	26.1	29.8	29.3	NT	NT	NT	NT	NT
BALL TACK (cm)	1.5-2.0	3.5	5.0	2.0	1.5	6.0->15	NT	NT	NT	NT	NT
SHEAR AT RT (hours)	>150	>150	>150	>150	>150	>150	NT	NT	NT	NT	NT
-carb. 25mm*12.5mm 1kg	>150	>150	>150	>150	>150	>150					
SHEAR AT 40°C (hours)											
-carb. 25mm*12.5mm 1kg	12h20'	42h	22h40'	9h30'	45h30'	17h30'	NT	NT	NT	NT	NT
SAFT (deg C)	94	99 cf		100	96 cf		NT	NT	NT	NT	NT
Brookfield viscosity at											
175°C (mPa.s)	189000	--	--	153000	--	--	NT		NT	NT	NT
-sp 27-0.5rpm	--	83000	89000	--	69000	70000					
-sp 27-1.0rpm											
Haake viscosity as function of temp.											
-ETA-T (170-200°C at 25 l/s)											
at 170°C (mPa.s)	221000	60000	77000	161000	56000	76000	330000	207000	249000	166000	151000
at 175°C (mPa.s)	157000	47000	60000	118000	39000	58000	NT	NT	NT	NT	NT
at 180°C (mPa.s)	112000	37000	46000	83000	30000	45000	167000	105000	119000	89000	83000
at 190°C (mPa.s)	50000	22000	28000	37000	20000	27000	86000	53000	61000	49000	47000
at 200°C (mPa.s)	29000	16000	18000	22000	16000	17000	44000	27000	30000	28000	27000

* Outside scope of the invention. NT - Not Tested. Haake for Ex. 7-11 is ETA-T (170-200°C at 1.5 l/s) af - adhesive failure. cf - cohesive failure.

TABLE 2

FORMULATION	EX. 12	EX. 13	EX. 14	EX. 15	EX. 2	EX. 1** *
V-4111 SIS	100	--	94	--	100	100
DPX-511 SIS	--	100	--	94	--	--
SI-Di Block	--	--	6	6	--	--
E-1310	--	--	--	--	--	120
E-2203	120	120	120	120	120	--
PROCESS OIL	--	--	--	--	10	10
ANTIOXIDANT	1	1	1	1	1	1
180 PEEL STRENGTH (N/CM) -steel	7.7	7.7	7.6	7.9	7.73	7.73
LOOP TACK (N/25mm) -steel	28.3	28.1	28.5	28.8	30.3	25.4
BALL TACK (cm)	1.5	1.5	1.5	1.5	3.5	1.5 - 2.0
SHEAR AT RT (hours) -carb. 25mm*12.5mm 1kg	>120 >120	>120 >120	>120 >120	>120 >120	>150 >150	>150 >150
SHEAR AT 40°C (hours) -carb. 25mm*12.5mm 1kg	13h 17' >50 >50 >50	22h 27' 27h 08' >50 >50	>50 >50 >50 >50	12h 06' 42h 56' 43h 00' >50	>24h 59'af >50 >50	>0h 49' >7h 15' >15h 01' >32h 22'
SAFT (deg C) -steel 25mm*12.5mm 0.5kg	96	95	95	94	99cf	94
Brookfield viscosity at 175°C (mPa.s) -sp 27-0.5rpm	69000	49000	54000	45000	83000	189,000

** Outside scope of Invention

TABLE 3

FORMULATION	EX. 16 BLEND 1	EX. 17 BLEND 2	EX. 18 BLEND 3	EX. 19 BLEND 4
DPX-511 SIS	100	100	100	100
E 2203	100	120	100	120
FLEXON 878	5	5	15	15
ANTIOXIDANT	1	1	1	1
180 peel adhesion (N/cm (steel))	6.47	7.67	6.00	6.67
Loop Tack (N/25 mm) (steel)	24.2	28.8	21.8	24.1
Ball tack (cm)	1.5	1.5	1.5	1.5
Shear on cardboard at 40°C 25 mm * 12.5 mm - 1 kg (hrs)	>50	45 h 30'	39	31 h
Soft (°C) Average	100.5	97.4	98.1	93.1
Blend viscosity at 175°C (cps) (spindle/rpm - after 2 hrs)	78800 (27/2.5)	59600 (27/2.5)	61000 (21/0.5)	39000 (21/0.5)
CARIFLEX TR 1107	100	100	100	100
E 2203	100	120	100	120
FLEXON 876	5	5	15	15
ANTIOXIDANT	1	1	1	1
180 peel adhesion (N/cm (steel))	6.08	7.45	5.47	6.40
Loop Tack (N/25 mm) (steel)	20.2	22.7	20.8	22.1
Shear on cardboard at 40°C 25 mm * 12.5 mm - 1 kg (hrs)	43h40'	24h20'	5h50'	5h10'
Soft (°C) Average	95	90.8	90.6	89.8
Blend viscosity at 175°C (cps) (Brookfield) (spindle/rpm - after 2 hrs)	163000 (27/1.0)	108000 (27/1.0)	105000 (27/1.0)	73200 (27/2.5)

TABLE 4

FORMULATION	EX. 20	EX. 21	EX. 22
	Quintac® 3450	V 4111 reference	DPX 511 reference
180° peel strength (N/cm) - steel	6.7	8.1	7.6
loop tack (N/25 mm) - steel	26.2	32.2	30.0
ball tack (cm)	1.5	1.5	2.0
shear at RT (hours)	>120	>120	>120
- cardb. 25 mm * 12.5 mm 1 kg	>120	>120	>120
shear at 40°C (hours)	34h00'af	36h03'af	>50
- cardb. 25mm * 12.5 mm 1 kg			
SAFT (°C)			
- steel 25 mm * 12.5 mm 0.5 kg	93 cf	101 cf	99 cf
Coating temperature (°C)	185	200	185
Brookfield viscosity at 175°C (mPa.s)	44000 (sp 2.7-2.5 rpm)	87000 (sp 2.7-1 rpm)	62000 (sp 2.7-1 rpm)

- 16 -

CLAIMS:

1. A hot melt pressure sensitive adhesive composition comprising a mixture of:
- 5
- a) 100 parts by weight of a thermoplastic elastomer having the structure $(S-I)_n$ S wherein S is substantially a polystyrene block, I is substantially a polyisoprene block and n is an integer of from 2 to 10 and wherein the content of polystyrene in said thermoplastic elastomer ranges from
- 10
- about 10 to about 30% by weight and wherein the number average molecular weight of said thermoplastic elastomer ranges from about 50,000 to about 500,000;
- 15
- b) from about 70 to about 150 parts by weight of a petroleum resin tackifier having a softening point in the range of from about 85°C to about 105°C, said resin being a Friedel Crafts Copolymer comprising:
- 20
- i) a petroleum feed comprising C₅ olefins and C₅ diolefins or a mixture of C₅ and C₆ olefins and diolefins, said feed being obtained from the cracking of petroleum feedstock, copolymerized with
- 25
- ii) from about 5 to 15% by weight, based on component (i), of one or a mixture of monovinyl aromatic compounds having 8-9 carbon atoms;
- 30
- said composition characterized as having a melt viscosity at 175°C of less than about 100,000 mPa.s as measured by ASTM-D3236.
2. The composition of Claim 1 wherein n is 2.
- 35
3. The composition of Claim 2 further containing from about 0.5 to about 25 parts by weight of an aromatic, naphthenic or paraffinic extender oil.

- 17 -

4. The composition of Claim 2 wherein said monovinylaromatic compound is styrene.
- 5 5. The composition of Claim 2 wherein said thermoplastic elastomer comprises a blend of at least two different block copolymers, one having a polystyrene block content of from about 10 to about 20% by weight and another having a different polystyrene block content of from about 15 to about 35% by weight.
- 10 6. The composition of Claim 2 further containing from about 0.05 to about 2 parts by weight of an antioxidant.
- 15 7. The composition of Claim 2 further containing from about 0.1 up to about 10 parts by weight of a di-block copolymer having the structure S-I, said di-block copolymer having a polystyrene content of from about 10 to about 30% by weight.
- 20 8. The composition of Claim 2 wherein said thermoplastic elastomer has a number average molecular weight in the range of from about 90,000 to about 250,000.
- 25 9. The composition of Claim 2 wherein said petroleum resin tackifier is present at a level of from about 90 to about 125 parts by weight.
- 30 10. The composition of Claim 2 wherein said petroleum resin has a softening point in the range of from 90°C to 100°C and a content of monovinyl aromatic monomer is the range of about 6 to 12% by weight.
- 30 11. The composition of Claim 2 wherein the melt viscosity of said composition is in the range of from about 35,000 to about 80,000 mPa.s.
- 35 12. A process for preparing an adhesive tape comprising:
 - a) heating the hot melt pressure sensitive adhesive composition of Claim 1 to a temperature in the range of from about 150°

- 18 -

C to about 200°C;

- 5 b) applying a thin coating of said melt to the surface of a tape substrate at a speed greater than or equal to 500 m/min. to form a coated substrate; and
- c) cooling said coated substrate.
- 10 13. An adhesive tape comprising a tape substrate having the adhesive composition of Claim 1 applied to one surface thereof at a dry thickness in the range of from about 10 to 65 g/cm².
14. The tape of Claim 13 wherein the adhesive surface of said tape is in contact with corrugated cardboard.

INTERNATIONAL SEARCH REPORT

Internat : Application No
PCT/US 94/14384A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09J153/02 C09J157/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 318 217 (EXXON CHEM. PAT. INC.) 31 May 1989 see page 14, column I, line 22-45 ---	1-14
X	WO,A,93 17079 (MINNESOTA MINING AND MANUF. CO.) 2 September 1993 see the whole document -----	1-14

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

21 April 1995

Date of mailing of the international search report

17. 05. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Glikman, J-F

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat : Application No

PCT/US 94/14384

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-318217	31-05-89	AU-A- 2585688	01-06-89
		DE-D- 3889429	09-06-94
		DE-T- 3889429	25-08-94
		JP-A- 2242873	27-09-90
WO-A-9317079	02-09-93	US-A- 5183705	02-02-93
		AU-B- 3780193	13-09-93
		CA-A- 2127535	02-09-93
		EP-A- 0628068	14-12-94